



# KÖSTER Repair Mortar

Technical Data Sheet W 530 025

Issued: 2020-10-27

RCC Test report N 141-3-81 Product Identification Characteristics according to BDS EN 1015 parts 10,11,18,21

# Fillet, repair and water-repellent finishing mortar

CE

KÖSTER BAUCHEMIE AG Dieselstraße 1-10, 26607 Aurich

13 W 530 EN 998-1:2010 Normal Plaster Mortar (R) EN 998-1:2010 ZA.1

Compressive strength 28 d CS IV
Capillary water uptake W0

Tensile strength ≥ 1.5 N/mm² failure type A/B

Dry density 1.50 - 1.80 kg/dm³ Depth of water penetration NPD

Coefficient of water vapor  $\mu \ge 20$  permeability

Reaction to fire

A1

#### **Features**

KÖSTER Repair Mortar is a watertight repair mortar and plaster with excellent adhesion even to old building material substrates. With the addition of KÖSTER SB Bonding Emulsion, it can be used as PCC (polymer-modified cement concrete) mortar.

#### **Technical Data**

Density of fresh mortar 1.8 kg / I Compressive strength after 24  $> 10 \text{ N} / \text{mm}^2$ Compressive strength after 7 days  $> 18 \text{ N} / \text{mm}^2$ Compressive strength after 28 days approx. 35 N / mm<sup>2</sup> Flexural tensile strength after 24  $> 2,5 \text{ N} / \text{mm}^2$ hours Flexural tensile strength after 7 > 4 N / mm<sup>2</sup>days Flexural tensile strength after 28  $> 6 N / mm^2$ 

Application of next layer after approx. 24 hours
E-Modulus approx. 19.000 N / mm²
Adhesive tensile strength > 1,5 N / mm²

#### **Fields of Application**

For carrying out watertight repairs and touch up, for creation of water-repellent plasters; for concrete repair. For evening out rough surfaces or joints prior to the application of bitumen thick film sealants, even under pressurized water. It can be used for fillets in the wall / floor junction which are stressed by pressurized water prior to the application of bitumen thick film sealants (KÖSTER Bikuthan 2C, KÖSTER Bikuthan 1C, KÖSTER Deuxan 2C, KÖSTER Deuxan Professional) and mineral based coatings (KÖSTER KD System, KÖSTER NB 1 Grey, etc).

#### Substrate

The surface has to be sound and solid, free of oil and grease. The material can be applied to all mineral substrates. Before installing the fillet on the external basement wall, brush on KÖSTER NB 1 Grey (consumption approx.  $4 \text{ kg} / \text{m}^2$ ). If larger surfaces are to be plastered,

a plaster key made of repair mortar and water / KÖSTER SB-Bonding-Emulsion (25 % admixture to the mixing water) should be applied beforehand.

When installing mortars substrate preparation is of vital importance. Pre-wet all mineral substrates before the installation of KÖSTER Repair Mortar. The surface near pore structure must be saturated, (avoiding standing water and puddles) so that it does not absorb water from the applied mortar. Highly absorbent substrates can be primed with KÖSTER Polysil TG 500.

#### **Application**

Mix 25 kg of KÖSTER Repair Mortar with 2.5 – 3.0 l water + 0.8 l of KÖSTER SB-Bonding Emulsion. The mortar has a pot life of approx. 3 hours. Apply KÖSTER Repair Mortar using customary mason tools. The material can also be prepared without the use of KÖSTER SB-Bonding Emulsion; in this case, add 1 liter of water instead.

Installation of fillets (stressed by pressurized water): The substrate has to be primed with KÖSTER NB 1 Grey (consumption: approx. 4 kg /  $\rm m^2$ ). Allow the KÖSTER NB 1 Grey to cure for at least 24 hours. Now the fillet can be installed (leg length of approx. 4 – 6 cm) using KÖSTER Repair Mortar (25 kg of KÖSTER Repair Mortar mixed with 2.5 – 3.0 l water + 0.8 l KÖSTER SB-Bonding Emulsion). After another 24 hours, the fillet can be coated with KÖSTER bitumen thick film waterproofings (e.g. KÖSTER Deuxan 2C).

#### Aftertreatment

Curing can be aided by covering the hardened material with polyethylene sheets. This reduces surface shrinkage tension especially when the material has been applied in thick layers.

## Consumption

Approx. 1.8 kg / I void

Approx.  $18 \text{ kg} / \text{m}^2$  per cm of layer thickness of the plaster

Approx. 2.5 kg / meter of fillet

#### Cleaning

Clean tools immediately after use with water.

#### **Packaging**

W 530 025 25 kg bag

#### Storage

Store the material in a dry environment. In originally sealed packages, the material can be stored for a minimum of 12 months.

#### Safet

Wear protective gloves and goggles when processing the material. Observe all governmental, state, and local safety regulations when processing the material.

## Related products

KÖSTER Polysil TG 500 Prod. code M 111
KÖSTER Hydrosilicate Adhesive SK Prod. code M 170 020

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu

KÖSTER Repair Mortar 1/2



KÖSTER Restoration Plaster Grey Prod. code M 661 025 KÖSTER Restoration Plaster White/Fast Prod. code M 663 KÖSTER Restoration Plaster White/Light Prod. code M 664 020 KÖSTER Hydrosilicate Board Prod. code M 670 KÖSTER Dachflex Prod. code R 260 020 KÖSTER KD System Prod. code W 219 KÖSTER NB 1 Grey Prod. code W 221 025 KÖSTER NB 2 White Prod. code W 222 025 KÖSTER NB 4000 Prod. code W 236 025 KÖSTER KBE Liquid Film Prod. code W 245 KÖSTER Bikuthan 2C Prod. code W 250 028 KÖSTER Bikuthan 1C Prod. code W 251 KÖSTER Deuxan 2C Prod. code W 252 032 KÖSTER Deuxan Professional Prod. code W 256 032 KÖSTER SB Bonding Emulsion Prod. code W 710

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu

KÖSTER Repair Mortar 2/2